


**PCT**WORLD INTELLECTUAL PROPERTY ORGANIZATION  
International Bureau

## INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification <sup>6</sup> : <b>C03C 3/078, 3/085, 3/087, 3/089, 3/091, 3/093</b>		<b>A1</b>	(11) International Publication Number: <b>WO 00/09456</b>
			(43) International Publication Date: 24 February 2000 (24.02.00)
(21) International Application Number: PCT/US99/16106			(81) Designated States: CN, JP, US, European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE).
(22) International Filing Date: 16 July 1999 (16.07.99)			
(30) Priority Data: 60/096,558 14 August 1998 (14.08.98) US			
(71) Applicant (for all designated States except US): CORNING INCORPORATED [US/US]; 1 Riverfront Plaza, Corning, NY 14831 (US).			
(72) Inventors; and (75) Inventors/Applicants (for US only): HARES, George, B. [US/US]; 31 E. Fourth Street, Corning, NY 14830 (US). KOHLI, Jeffrey, T. [US/US]; 25 Spencer Hill Road, Corning, NY 14830 (US). WEBB, James, E. [US/US]; 102 High Road, Corning, NY 14830 (US).			
(74) Agent: PETERSON, Milton, M.; Patent Dept., SP TI 3-1, Corning Incorporated, Corning, NY 14831 (US).			

(54) Title: LEAD-FREE GLASSES



## (57) Abstract

This invention relates to lead-free silicate glasses that find use in producing fine crystal glassware and in laminated ware applications. The glasses consist essentially, in weight percent, of: SiO<sub>2</sub> 52-66; Al<sub>2</sub>O<sub>3</sub> 0-4; Li<sub>2</sub>O 0-4; Na<sub>2</sub>O 3-16; K<sub>2</sub>O 0-12; ZnO 15-30; BaO 0-7; MgO+CaO+SrO 0-4; ZrO<sub>2</sub> 0-4; B<sub>2</sub>O<sub>3</sub> 0-4.

**FOR THE PURPOSES OF INFORMATION ONLY**

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Larvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece			TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	NZ	New Zealand		
CM	Cameroon			PL	Poland		
CN	China	KR	Republic of Korea	PT	Portugal		
CU	Cuba	KZ	Kazakstan	RO	Romania		
CZ	Czech Republic	LC	Saint Lucia	RU	Russian Federation		
DE	Germany	LI	Liechtenstein	SD	Sudan		
DK	Denmark	LK	Sri Lanka	SE	Sweden		
EE	Estonia	LR	Liberia	SG	Singapore		

## LEAD-FREE GLASSES

### FIELD OF THE INVENTION

5           Lead-free glasses having properties that render them useful for production of crystal glassware and laminated ware.

### BACKGROUND OF THE INVENTION

10           Silicate glasses, having a relatively high content of lead oxide in their compositions, have unique properties that particularly adapt them to use in production of crystal glassware. The properties of interest include a low liquidus temperature and a long viscosity range. These properties avoid the occurrence of devitrification during forming processes.

15           Environmental and health concerns have led to a desire to eliminate, insofar as possible, use of toxic oxides, in particular lead oxide, in glass compositions. United States Patent No. 5,270,269 (Hares et al.) describes one approach to meeting this desirable end in the production of crystal glassware. The present invention provides a different approach.

20           The production of crystal glassware is usually a hand crafting operation. This involves several cycles of working and reheating a glass shape. It is, of course, desirable to complete as much of the shaping operation as possible during each cycle. This requires a low, liquidus temperature and a long, viscosity curve. The latter property translates into a long working range of

temperatures without devitrification, that is, without any crystal formation in or on the glass.

Other properties of interest in crystal glassware include high refractive index, dispersion, and density values; also, good scratch resistance, and high chemical durability, that is, resistance to chemical attack and weathering.

Another property of particular interest in thin-walled artware is the resonating sound that occurs when the rim of an article is lightly struck with another body such as a table utensil. This resonating sound is commonly known as the sonority, or ring, of a thin-walled article, such as a vase or goblet.

It is a purpose of the present invention to provide a family of glass compositions possessing properties useful both for crystal glassware and for laminated ware.

It is another purpose to provide a family of glass compositions free of toxic materials, in particular, free from lead compounds.

It is a further purpose to provide glasses having a CTE of  $70-110 \times 10^{-7}/^{\circ}\text{C.}$ , a density of at least  $2.70 \text{ g/cm}^3$ , a long viscosity curve, and a low liquidus value, such glasses being especially suited to production of crystal glassware.

It is a still further purpose to provide a family of glasses, as an alternative to the family disclosed in United States Patent No. 5,270,269, for the production of crystal glassware.

### SUMMARY OF THE INVENTION

The invention resides in part in a glass that is essentially lead-free, that exhibits a density of at least  $2.70 \text{ g/cm}^3$ , a liquidus below  $1000^{\circ} \text{C.}$ , a long viscosity curve, a CTE of  $70-110 \times 10^{-7}/^{\circ} \text{C.}$ , good scratch resistance, and chemical durability, and that has a composition, expressed in terms of weight percent on an oxide basis, consisting essentially of:

<b>SiO<sub>2</sub></b>	52-66	<b>ZnO</b>	15-30
<b>Al<sub>2</sub>O<sub>3</sub></b>	0-3	<b>BaO</b>	0-7
<b>Li<sub>2</sub>O</b>	0-4	<b>MgO+CaO+SrO</b>	0-5
<b>Na<sub>2</sub>O</b>	3-16	<b>ZrO<sub>2</sub></b>	0-4
<b>K<sub>2</sub>O</b>	0-12		

The invention further resides in an article of crystal glassware molded from the above glass; also, in an article in which surfaces of two bodies are joined by laminating.

5

### DESCRIPTION OF THE INVENTION

The glass family of the present invention was developed for use in production of crystal glassware. It represents an alternative to the glass family disclosed in the -269 patent for that purpose. While the present glass family is well-suited to that purpose, it has also been found to have properties adapted to certain glass laminating processes.

The glass composition of the earlier Hares et al. patent, is characterized by substantial contents of BaO and SrO with lesser amounts of ZnO. The present glass family requires neither BaO or SrO. At most, the presence of these oxides is permitted in limited amounts. Rather, the present glasses contain a relatively large amount of ZnO in contrast to the earlier glasses.

The present glasses are characterized by a low, liquidus temperature and a long, viscosity curve. The optimum viscosity for working an art glass is accepted as about  $10^4$  Pa.s ( $10^5$  poises). This may also be stated as Log Viscosity in Pa.s equals 4. The present glasses will have this viscosity at temperatures in the range of 850° C. to 900° C. A long viscosity curve is measured in terms of the temperature range over which the glass viscosity varies by no more than a factor of 10 from the optimum value of  $10^4$  Pa.s, e.g., a temperature range of 750° to 975° C.

The single FIGURE in the accompanying drawing is a graphical representation showing the viscosity/temperature curves for three different glasses. In the FIGURE, temperature (T), in degrees C., is plotted on the horizontal axis. Log viscosity, in Pa.s, is plotted on the vertical axis.

Curve A is the viscosity-temperature curve for the glass of Example 17 in TABLE I, infra. It illustrates a long, shallow curve typical of the present

glasses. Curve B is the curve for a borosilicate glass having a typical, steep viscosity-temperature, curve. Curve C is the curve for a typical, soda lime silicate glass.

It will be observed that the curvatures of Curves A and C are very similar with Curve C being a bit elevated. This indicates a slightly harder glass, that is a glass that is a bit more viscous at any given temperature. Thus, the two glasses would match well for coating or laminating purposes.

In addition, for art glass purposes, the present glasses have a liquidus below about 1000° C., preferably below 900° C. They also exhibit good chemical durability, and scratch resistance, as measured by Knoop hardness, with values preferably above 430. They should also have a density of at least 2.7 g/cm<sup>3</sup>, and a high refractive index.

A property of particular interest, the sonority, or ring, of the glass, is facilitated by having the alkali metal oxides Na<sub>2</sub>O and K<sub>2</sub>O present in equal molar amounts. Likewise, if Li<sub>2</sub>O is present, all three alkali metal oxides are preferably present in equal molar amounts. In terms of weight percent, the preferred alkali metal oxide ratios approximate 3K<sub>2</sub>O:2Na<sub>2</sub>O:1Li<sub>2</sub>O.

For laminating purposes, the important properties are CTEs of 70-110 x 10<sup>-7</sup>/° C., a low liquidus temperature and freedom of the composition from toxic oxides, particularly lead oxide. The glasses should also have closely matching viscosity-temperature curves. Preferably, the Log viscosity values differ by not more than about 0.5 over the entire temperature range.

The glasses are basically silicates with SiO<sub>2</sub> being the primary glass former. Broadly, glasses having properties suitable for present purposes consist essentially of, in weight percent as calculated from the batch on the oxide basis: 52-66% SiO<sub>2</sub>, 0-3% Al<sub>2</sub>O<sub>3</sub>, 0-4% ZrO<sub>2</sub>, 0-4% B<sub>2</sub>O<sub>3</sub>, 0-4% Li<sub>2</sub>O, 3-16% Na<sub>2</sub>O, 0-12% K<sub>2</sub>O, 15-30% ZnO, 0-7% BaO and 0-5% MgO+CaO+SrO. In addition, up to 5% of one or more oxides selected from Y<sub>2</sub>O<sub>3</sub>, La<sub>2</sub>O<sub>3</sub>, Nb<sub>2</sub>O<sub>5</sub>, and Ta<sub>2</sub>O<sub>5</sub> may be present, primarily to improve density and/or refractive index.

A feature of the invention is the replacement of lead oxide by zinc oxide. This replacement, in conjunction with control of the alkali metal oxides,

provides the desired viscosity and liquidus characteristics previously attained with lead oxide. The present glasses, containing zinc oxide, have much better scratch resistance than prior glasses containing lead oxide. They also provide improved chemical and weathering durability.

At least 3%  $\text{Na}_2\text{O}$  is required and up to 16% may be present. The alkali metal oxides contribute a relatively high CTE. While  $\text{K}_2\text{O}$  and  $\text{LiO}_2$  are not required, it is highly desirable to have a mixture of the three alkaline metal oxides present to provide the sonority property; also good electrical resistance where that property is a factor.

$\text{Al}_2\text{O}_3$  stabilizes the glass and improves chemical durability. Accordingly, at least 0.5% and preferably 1% are present. However, it stiffens the glass and pushes the viscosity curve higher.  $\text{ZrO}_2$  has a similar effect and must be limited.

$\text{B}_2\text{O}_3$  lowers the CTE and may be used for that purpose. However, it is preferably absent, and the total  $\text{R}_2\text{O} + \text{B}_2\text{O}_3$  preferably does not exceed about 16%.

While not required,  $\text{BaO}$  serves to increase CTE and density. Accordingly, up to 7%  $\text{BaO}$  may be employed. The remaining alkaline earth metal oxides,  $\text{MgO}$ ,  $\text{CaO}$  and  $\text{SrO}$  add nothing in particular to the present glasses, but may be present up to about 4-5%.

As indicated subsequently in TABLE I, compositions in which at least 97% consists of the following, somewhat narrower, component ranges, in weight %, are preferred for optimum properties:

$\text{SiO}_2$	56-63%	$\text{ZnO}$	15-25%
$\text{Al}_2\text{O}_3$	1-3%	$\text{BaO}$	0-7%
$\text{Li}_2\text{O}$	0-3%	$\text{MgO} + \text{CaO} + \text{SrO}$	0-4%
$\text{Na}_2\text{O}$	4-16%	$\text{B}_2\text{O}_3$	0-2%
$\text{K}_2\text{O}$	0-11%		

## SPECIFIC EMBODIMENTS

TABLE I records a group of glass compositions, expressed in terms of weight percent on the oxide basis, illustrating the compositional parameters of the present invention.

TABLE I

Wt%	1	2	3	4	5	6	7	8	9	10
SiO <sub>2</sub>	61.7	61.7	59.4	59.4	57.2	57.2	52.7	59.2	58.2	62.2
Al <sub>2</sub> O <sub>3</sub>	2.0	2.0	2.0	2.0	2.0	2.0	2.0	2.0	1.0	1.6
Li <sub>2</sub> O	0.0	2.6	0.0	2.5	0.0	2.5	0.0	0.0	2.5	2.3
Na <sub>2</sub> O	16.0	5.3	15.8	5.3	15.5	5.2	15.0	7.7	5.2	4.8
K <sub>2</sub> O	0.0	8.1	0.0	8.0	0.0	7.8	0.0	11.6	7.8	7.3
ZnO	20.0	20.0	22.5	25.0	25.0	25.0	30.0	19.1	25.0	21.4
Liquid Temp (°C)	890	840	855	885	880	995	1025	940	945	900
Soft. Pt. (°C)	713	652	709	655	703	647	684	737	644	678
Anneal Pt. (°C)	537	483	544	487	542	489	544	544	486	498
Strain Pt. (°C)	494	443	503	447	501	450	506	499	447	457
CTE (x10 <sup>-7</sup> /°C)	91.6	87.4	90.6	86.9	90.3	87.2	90.4	103.6	88.5	81.1
Density (g/cm <sup>3</sup> )	2.74	2.73	2.79	2.76	2.82	2.82	2.93	2.73	2.87	2.74

TABLE I (cont'd)

Wt%	11	12	13	14	15	16	17	18
SiO <sub>2</sub>	67.2	63.6	63.9	62.2	61.6	61.0	62.0	61.8
Al <sub>2</sub> O <sub>3</sub>	1.7	1.6	1.6	1.5	2.1	1.5	1.6	1.5
Li <sub>2</sub> O	7.4	2.6	2.8	0.0	2.6	2.2	2.3	0.9
Na <sub>2</sub> O	-	5.3	5.8	14.2	5.3	4.6	4.7	7.5
K <sub>2</sub> O	-	8.1	8.8	0.0	8.1	7.0	7.2	7.1
ZnO	18.7	18.4	16.5	17.4	19.9	18.2	17.3	18.5
BaO	5.0	0.0	0.0	4.7	0.0	0.0	4.7	2.3
La <sub>2</sub> O <sub>3</sub>	-	-	-	0.0	0.0	4.9	0.0	0.0
Liquid Temp (°C)	1230	860	855	975	890	880	810	870
Soft. Pt. (°C)	-	660	647	698	658	679	674	699
Anneal Pt. (°C)	481	481	469	531	483	501	483	504
Strain Pt. (°C)	449	442	430	491	445	459	441	461
CTE (x10 <sup>-7</sup> /°C)	66.4	88.9	93.5	90.8	89.2	81.7	88.7	92.6
Density (g/cm <sup>3</sup> )	2.73	2.70	2.67	2.75	2.72	2.79	2.77	2.75

The TABLE also reports the softening point (S.P.), annealing point (A.P.), and strain point (St.P.) in ° C., the linear coefficient of thermal expansion (CTE) over the temperature range of 25-300° C. expressed in terms of x 10<sup>-7</sup>/° C., and the density (Den) in grams/cm<sup>3</sup>, as determined in accordance with measuring techniques conventional in the glass art.

Compositions 7 and 11 are comparative examples. Composition 7 illustrates the effect of a low SiO<sub>2</sub> content with maximum Na<sub>2</sub>O and ZnO contents. Composition 11 illustrates the effect of a high SiO<sub>2</sub> content in



conjunction with no Na<sub>2</sub>O content. The glass of composition 11 phase separated during an attempt to measure the softening point.

The sound, or ring, of a glass, like any musical sound, is a matter of individual taste. Nevertheless, we have found that the degree, or efficiency, of glass resonance can be quantified. In such quantifications, the principles of resonant ultrasound spectroscopy (RUS), as described in a publication by Migliori and Sarrao, Resonant Ultrasound Spectroscopy, John Wiley and Sons, Inc., New York (1997), were employed.

The resonant quality (Q) of a material may be measured by various techniques. However, we have found that RUS equipment provides a simple means of obtaining experimental data having a high quality. The Q value is determined at a given frequency by a peak-fitting procedure.

Effectively, the resonant frequency is divided by the width of a peak at one half maximum power. The scan range is narrowed to focus on a single peak. The equipment scans display peaks at a constant phase angle. This angle is adjusted to obtain a symmetric peak prior to measurement of the peak width.

Numerous, resonant frequencies can be measured by scanning an appropriate, frequency range. It was found adequate to use an average of the first three modes for comparative purposes. Test pieces of glass, in the form of 10x8x6 mm, rectangular prisms, were prepared and tested. TABLE II sets forth the average Q values determined for several glasses having compositions in the R<sub>2</sub>O-ZnO-BaO-SiO<sub>2</sub> family. The ratio of the R<sub>2</sub>O oxides, in the order of LiO<sub>2</sub>:Na<sub>2</sub>O:K<sub>2</sub>O in mol %, is shown for each composition. The compositions are identified by the numerical designation employed in TABLE I.

Measurements made on two different glasses, designated NIST 711 and HPFS, are shown for reference purposes. NIST 711 is a lead glass used as a viscosity standard by the National Institute of Standards and Technology. HPFS is a high purity, fused silica glass.

TABLE II

Glass	Q Value	R <sub>2</sub> O Ratio
19	4000	1:1:1
14	3935	1:1:1
20	3887	1:4:2.5
11	3446	1:0:1
8	3112	0:1:1
13	1854	0:0:1
12	1833	1:0:0
16	1016	0:1:0
NIST	3600	-
HPFS	6600	-

It is apparent that efficiency is favored by a mixture of the three R<sub>2</sub>O oxides. A mixture of two is not as efficient, but adequate. A single alkali metal oxide is generally not adequate regardless of the alkali metal. As a rule of thumb, a glass should have a Q value of at least 3,000 to be considered efficient. Preferably, the value is above 3,500.

The chemical durability of the glasses against acids is defined in terms of weight loss (W.L.A.). Values were determined by immersing polished plates of known weight for 24 hours in an aqueous bath of 5% by weight HCl operating at 95° C. After withdrawal from the bath and drying, the plates were re-weighed and the weight loss measured in terms of mg/cm<sup>2</sup>.

The chemical durability of the glass against bases is defined in terms of weight loss (W.L.B.). Values were determined by immersing plates of known weight for six hours in an aqueous bath of 0.02 N Na<sub>2</sub>CO<sub>3</sub> operating at 95° C. After withdrawal from the bath and drying, the plates were re-weighed and the weight loss measured in terms of mg/cm<sup>2</sup>.

Three of the glasses shown in TABLE I, and the first glass shown in the Hares et al. -269 patent, were melted. Test pieces were prepared for determining acid and basic durability by the methods just described. The results are shown in TABLE III.

TABLE III

Durability	19	20	8	-269
Acid	0.032	0.083	0.60	0.13
Basic	0.038	0.060	0.062	0.087

The actual, batch ingredients for preparing the glasses can comprise any materials, either oxides or other compounds, which, when melted together, will be transformed into the desired oxide in the proper proportions. For example,  $K_2CO_3$ , and  $Na_2CO_3$  can provide the sources of  $K_2O$  and  $Na_2O$ , respectively.  $Sb_2O_3$  (not shown) may be included to perform its conventional function in glass melting as a fining agent.

The batch components were mixed together very thoroughly to assist in securing a homogeneous melt, and that mixture was charged into platinum crucibles. The crucibles were moved into a furnace operating at about 1450°C. and the batches melted for about three hours. Thereafter, the melts were poured into steel molds to form rectangularly-shaped slabs of glass having dimensions of about ~ 25.4 x 10.16 x 1.27cm (10" x 4 x 0.5"). Those slabs were transferred immediately to an annealer operating at about 500° C.

Whereas the above description reflects laboratory melting and forming practice only, it must be appreciated that the compositions recited in TABLE I, complying with the terms of the subject invention, can be melted and formed in much larger quantities utilizing conventional, commercial melting units and glass forming techniques.

WE CLAIM:

1. A glass that is essentially free from lead, that exhibits a density of at least  $2.70 \text{ g/cm}^3$ , a liquidus below  $1000^\circ \text{ C.}$ , and a long viscosity curve, a coefficient of thermal expansion in the range  $70\text{-}110 \times 10^{-7}/^\circ \text{ C.}$ , good scratch resistance and chemical durability, and that has a composition, expressed in terms of weight percent on an oxide basis of:

<b>SiO<sub>2</sub></b>	<b>52-66</b>	<b>ZnO</b>	<b>15-30</b>
<b>Al<sub>2</sub>O<sub>3</sub></b>	<b>0-4</b>	<b>BaO</b>	<b>0-7</b>
<b>Li<sub>2</sub>O</b>	<b>0-4</b>	<b>MgO+CaO+SrO</b>	<b>0-5</b>
<b>Na<sub>2</sub>O</b>	<b>3-16</b>	<b>ZrO<sub>2</sub></b>	<b>0-4</b>
<b>K<sub>2</sub>O</b>	<b>0-12</b>	<b>B<sub>2</sub>O<sub>3</sub></b>	<b>0-4</b>

2. A glass in accordance with claim 1 which contains at least 0.5% Al<sub>2</sub>O<sub>3</sub>.

3. A glass in accordance with claim 1 in which the total of Na<sub>2</sub>O+K<sub>2</sub>O+Li<sub>2</sub>O+B<sub>2</sub>O<sub>3</sub> does not exceed about 16%.

4. A glass in accordance with claim 1 which contains the three alkali metal oxides, K<sub>2</sub>O, Na<sub>2</sub>O and Li<sub>2</sub>O in the molar ratio of 1:1:1.

5. A glass in accordance with claim 1 having a composition, expressed in weight percent on an oxide basis, in which at least 97% consists essentially of 56-63% SiO<sub>2</sub>, 1-3% Al<sub>2</sub>O<sub>3</sub>, 0-4 Li<sub>2</sub>O, 4-16% Na<sub>2</sub>O, 0-11% K<sub>2</sub>O, 15-25% ZnO, 0-7% BaO, 0-4% MgO+CaO+SrO and 0-2% B<sub>2</sub>O<sub>3</sub>.

6. An article of crystal glassware in which the glass is essentially free from lead, that exhibits a density of at least  $2.70 \text{ g/cm}^3$ , a liquidus below  $1000^\circ \text{ C.}$ , and a long viscosity curve, a coefficient of thermal expansion in the range  $70\text{-}110 \times 10^{-7}/^\circ \text{ C.}$ , good scratch resistance and chemical durability, and that has a

composition, expressed in terms of weight percent on an oxide basis of:

SiO <sub>2</sub>	52-66	ZnO	15-30
Al <sub>2</sub> O <sub>3</sub>	0-4	BaO	0-7
Li <sub>2</sub> O	0-4	MgO+CaO+SrO	0-5
Na <sub>2</sub> O	3-16	ZrO <sub>2</sub>	0-4
K <sub>2</sub> O	0-12	B <sub>2</sub> O <sub>3</sub>	0-4

7. An article in accordance with claim 6 in which the glassware has a sonority efficiency of at least 3,000.

5

8. An article in accordance with claim 6 in which the glass contains at least 0.5% Al<sub>2</sub>O<sub>3</sub>.

9. An article in accordance with claim 6 in which the total content of Na<sub>2</sub>O+K<sub>2</sub>O+Li<sub>2</sub>O+B<sub>2</sub>O<sub>3</sub> does not exceed 16%.

10

10. An article in accordance with claim 6 in which the glass composition contains the three alkali metal oxides, K<sub>2</sub>O, Na<sub>2</sub>O and Li<sub>2</sub>O in a molar ratio of 1:1:1.

15

11. An article in accordance with claim 6 in which the glass has a composition, expressed in weight percent on an oxide basis, in which at least 97% consists essentially of 56-63% SiO<sub>2</sub>, 1-3% Al<sub>2</sub>O<sub>3</sub>, 0-4 Li<sub>2</sub>O, 4-16% Na<sub>2</sub>O, 0-11% K<sub>2</sub>O, 15-25% ZnO, 0-7% BaO, 0-4% MgO+CaO+SrO and 0-2% B<sub>2</sub>O<sub>3</sub>.

20


12. A laminated, glass article comprising two glass components joined directly to each other, one component being a glass that is essentially free of lead, that exhibits a density of at least 2.70 g/cm<sup>3</sup>, a liquidus below 1000° C., and a long viscosity-temperature curve, a coefficient of thermal expansion in the range 70-110 x 10<sup>-7</sup>/° C., good scratch resistance and chemical durability,

25

and that has a composition, expressed in terms of weight percent on an oxide basis of:


<b>SiO<sub>2</sub></b>	52-66	<b>ZnO</b>	15-30
<b>Al<sub>2</sub>O<sub>3</sub></b>	0-4	<b>BaO</b>	0-7
<b>Li<sub>2</sub>O</b>	0-4	<b>MgO+CaO+SrO</b>	0-5
<b>Na<sub>2</sub>O</b>	3-16	<b>ZrO<sub>2</sub></b>	0-4
<b>K<sub>2</sub>O</b>	0-12	<b>B<sub>2</sub>O<sub>3</sub></b>	0-4,

the other component being a glass having a different composition, but having a long viscosity-temperature curve that closely matches that of the first glass over the entire temperature range.



## INTERNATIONAL SEARCH REPORT

International application No.  
PCT/US99/16106

<b>A. CLASSIFICATION OF SUBJECT MATTER</b> IPC(6) :C03C 3/078, 3/085, 3/087, 3/089, 3/091, 3/093 US CL :501/65, 66, 67, 68, 698, 70, 72 According to International Patent Classification (IPC) or to both national classification and IPC		
<b>B. FIELDS SEARCHED</b> Minimum documentation searched (classification system followed by classification symbols) U.S. : 501/65, 66, 67, 68, 698, 70, 72 Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)		
<b>C. DOCUMENTS CONSIDERED TO BE RELEVANT</b>		
Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	EP 553 586 A (CORNIER et al.) 04 August 1993, see the translated Abstract.	1-3, 5-9 and 11
X	US 4,106,946 (RITZE) 15 August 1978, see the Abstract.	1-5
A	US 5,270,269 A (HARES et al.) 14 December 1993, Abstract.	1-11
<input type="checkbox"/> Further documents are listed in the continuation of Box C. <input type="checkbox"/> See patent family annex.		
* Special categories of cited documents: *A* document defining the general state of the art which is not considered to be of particular relevance *E* earlier document published on or after the international filing date *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified) *O* document referring to an oral disclosure, use, exhibition or other means *P* document published prior to the international filing date but later than the priority date claimed	*T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art *A* document member of the same patent family	
Date of the actual completion of the international search 25 AUGUST 1999		Date of mailing of the international search report 07 SEP 1999
Name and mailing address of the ISA/US Commissioner of Patents and Trademarks Box PCT Washington, D.C. 20231 Facsimile No. (703) 305-3230		Authorized officer DAVID SAMPLE  Telephone No. (703) 308-0661